


Gear Hob Blanks



Gear Hob Blanks

Grade	ISO code(s)	Co (±0.5%)	Grain Size	Density (g/cm ³) ±0.1	Hardness (HRA) ±0.5	TRS (Kgf/mm ²)	Area of application
WF08	K01	8	Ultrafine	14.53	94.0	380	Hard hobbing >60HRC
NEW!! TF25+	K10-K20	11	Ultrafine	14.15	92.3	380	Hard hobbing up to 58HRC
WF25	K10-K20	11.5	Ultrafine	14.15	92.2	380	Hard hobbing up to 42HRC
WF15	K20-K40	10	Submicron	14.35	91.8	380	Soft hobbing up to 35HRC
K200	K20-K40	10	Submicron	14.40	91.5	400	Soft hobbing up to 35HRC

Grade development as per customer's requirement



All blanks for hobs are manufactured as per customers' specification.



■ **CB-CERATIZIT (Taiwan) Group Head Office**

ADD: 3F, NO. 217, Sec.2, New Taipei Blvd., Hsin Chuang Dist., New Taipei City 24250, Taiwan (R.O.C.)

TEL: + 886-2-8521-6688 FAX: + 886-2-8521-1011

E-mail: sales@cbceratizit.com

■ **CB-CERATIZIT (Xiamen) China Head Office**

ADD: 69 Xingxi Rd., Xinglin, Jimei, Xiamen, China, 361022

TEL: +86-592-666-1000 FAX: +86-592-621-9599

E-mail: sales@cbceratizit.com