


# Gear Hob Blanks

Grade	ISO code(s)	Co (±0.5%)	Grain Size	Density (g/cm <sup>3</sup> ) ±0.1	Hardness (HRA) ±0.5	Area of application
K160	K05	8.0	Ultrafine	14.48	93.5	Hard hobbing >60HRC
<b>NEW!!</b> WF24	K10-K20	12.0	Ultrafine	14.06	92.2	Hard hobbing up to 58HRC
WF15	K20-K40	10.0	Submicron	14.35	91.8	Soft hobbing up to 35HRC
K200	K20-K40	10.0	Submicron	14.40	91.5	Soft hobbing up to 35HRC



All blanks for hobs are manufactured as per customers' specification.



■ **CB-CERATIZIT (Taiwan) Group Head Office**

ADD: 3F., NO. 217, Sec.2, New Taipei Blvd., Hsin Chuang Dist., New Taipei City 24250, Taiwan (R.O.C.)

TEL: + 886-2-8521-6688 FAX: + 886-2-8521-1011


E-mail: sales@cbceratizit.com

■ **CB-CERATIZIT (Xiamen) China Head Office**

ADD: 69 Xingxi Rd., Xinglin, Jimei, Xiamen, China, 361022

TEL: +86-592-666-1000 FAX: +86-592-621-9599

E-mail: sales@cbceratizit.com



# WEAR PROTECTION

Gear Hob Blanks